

FilaPLA Filament

FilaPLA - FILATECH HEAVY DUTY POLYLACTIC ACID FILAMENT

PLA (Polylactic Acid) is one of the two most commonly used desktop 3D printing filaments (with the other being ABS filament). It is the "default" recommended material for many desktop 3D printers, and with good reason - PLA is useful in a broad range of printing applications, has the virtue of being both odorless and low-warp, and does not require a heated bed.

Beside all good properties of PLA filaments, like superb printing quality and easiest print setup, there are some downsides as well. PLA has almost the least temperature resistance and low toughness compare to other filaments. It starts deforming above 60 °C and it is also brittle with low toughness.

FilaPLA is PLA-based copolymer. FilaPLA filaments have been developed by our engineers at Filatech to overcome the weaknesses of the normal PLA by combining the toughness of ABS and temperature resistance of PC with the advantages of normal PLA

FilaPLA is very easy to print, heated bed is not necessary and depending to the design of the printing parts, it might be needed up to 50 °C just like normal PLA.

FilaPLA withstands up to 100 °C of working temperature (20 °C higher than ABS) and it's much tougher than normal PLA.

Our FilaPLA filaments for 3D Printing are available in a wide range of colors in both 1.75mm and 2.85mm diameter.

OPTIONS:

Size: 1.75 mm -/+ 0.03 mm

2.85 mm -/+ 0.03 mm

Color: Full Color Range (Special Colors By Order)

Packaging: 0.5 Kg Spools

1.0 Kg Spools

6.0 Kg Spools

FEATURES:

PLA based compound

100% bio-based, bio-compostable Low melting point for easier printing

Lower shrinkage rate Higher HDT up to 100 °C

High rigidity with good flex which brings higher toughness compare to normal PLA

Less brittle and easy storage

Dimensional stability which produces higher quality prints

Good bridging ability

Delicate/Sharp edge printing

Excellent printing quality at low process temperature

Can be printed without heated bed.

No chemical odors produced during printing

SPECIFICATIONS:

Filament Material: FilaPLA

Specific Gravity: 1.30 gr/cm³

Size: 1.75 mm -/+ 0.03 mm 2.85 mm -/+ 0.03 mm

Printing Information: Extruder: 210 – 230 °C

Bed: 40-60 °C (Only for big parts)

Working Temperature: Up to 100 °C (Max. HTD is achievable after post annealing @80 °C for 30

min)

FilaPLA Filament

ENGINEERING PROPERTIES:

Properties	Test Method	Unit	Value
Specific Gravity	ASTM D792	gr/cm ³	1.3
Melt Index 2,160 gr @ 190°C	ASTM D1238	gr/10min	5
Tensile Strength @ Break 50mm/min (2 inch/min)	ASTM D638	Mpa (kgf/cm²)	42 (430)
Elongation @ Break 50mm/min (2 inch/min)	ASTM D638	%	8
Izod Impact Test Notched @ 23 °C	ASTM D256	J/m	40
Heat Distortion Temperature @0.455 Mpa (66 psi)	ASTM D648	°C	100*

^{*}When fully crystalized

CERTIFICATES:

Management : BS EN ISO 9001:2015
Quality: CE (CE-2924)
Environment: RoHS (UQ-5724)

PLA طراحی و ساخت شرکت فیلاتک و تولید شده از یک کوپولیمر مهندسی بر پایه FilaPLA فیلامنت PLA طراحی و ساخت شرکت فیلاتک و عبارتی یک PLA می باشد Super PLA یا به عبارتی یک PLA می باشد Super PLA بسادگی معمولی در دمای پایین پرینت می شود و در اکثر موارد بسته به ابعاد و طرح قطعه، PLA بسادگی معمولی در دمای پایین پرینت می شود و در اکثر موارد بسته به ابعاد و طرح قطعه، PLA بسادگی معمولی در دمای پایین پرینت می شود و در اکثر موارد بسته به ابعاد و طرح قطعه،

عبارتند از: چسبندگی عالی بین لایه های FiaPLA در کنار کیفیت بالای پرینت، خواص استثنایی پرینت - استحکام مکانیکی بسیار بالا - مقاومت به درجه حرارت بسیار بالا تا 100 درجه سانتیگراد حداقل انقباض ابعادی حین پرینت و بدون تابخوردگی - انعطاف پذیری - (ABS درجه بالاتر از 20) معمولی - بدون تردی و PLA مناسب در تلفیق با استحکام بالا و در نتیجه چقرمگی بسیار بالاتر از معمولی - قابلیت ماشینکاری و سمباده زنی بسیار عالی PLA شکنندکی رایج در قطعات تولیدی از می باشد. حداکثر مقاومت حرارتی بعد از Post Processing در مواردی که نیاز به عملیات تمام کاری شود می باشد. حداکثر مقاومت حرارتی بعد از 30.

در عکسهای محصول ارایه شده است. کلیه فیلامنتهای تولیدی FilaPLA مشخصات کامل مهندسی فیلاتک دارای گواهینامه کیفیت تولید و سازگاری با محیط زیست از اروپا میباشند. Made in UAE.